## Soft X-ray spectroscopy of electrochemical interfaces

## **Robert Weatherup**

## Department of Materials, University of Oxford

Lithium-ion batteries (LIBs) are key to the transition from fossil fuels towards increased use of renewable energy sources. However, more widespread deployment requires improvements in energy density, cost and cycle-lifetime. Various cathode and anode materials are under consideration for next-generation LIBs, and the interfacial stability of these materials in contact with the electrolyte is a critical consideration. Interface-sensitive *operando* characterization techniques are urgently needed to reveal the reactions occurring in working batteries.<sup>1,2</sup>

I will present our recent *ex-situ* studies of Ni-rich LiNi<sub>x</sub>Mn<sub>y</sub>Co<sub>1-x-y</sub>O<sub>2</sub> (NMC) cycled vs. Graphite in full cells, where electrochemical signatures of cell degradation are linked to surface chemistry changes taking place on the electrodes as revealed with Hard X-ray Photoelectron Spectroscopy (HaXPES). This reveals thickening of electrode-electrolyte interphases with cycling, the growth of a reduced surface layer at the cathode, and incorporation of transition metals at the anode due to crossover from cathode.

Despite these insights, ex-situ measurements nevertheless can't capture the intermediate species involved in interface degradation. We therefore introduce several *operando* approaches for resolving the structural and chemical evolution of electrochemical interfaces.<sup>3-8</sup> This includes *in situ* deposition of thin lithium layers onto solid electrolytes,<sup>6,7</sup> and enclosed reaction cells sealed with thin (<100 nm) X-ray-transparent silicon nitride membranes that allow studies with liquid electrolytes.<sup>8</sup> We demonstrate how these approaches can monitor reactions at electrode-electrolyte interfaces under electrochemical control, including solid-electrolyte interphase (SEI) formation on Li-ion battery anodes.

## References

- 1. Wu et al. Phys. Chem. Chem. Phys. 2015, 17, 30229.
- 2. Weatherup et al. Top. Catal. 2018, 61, 2085.
- 3. Velasco-Velez et al. Angew. Chemie 2015, 54, 14554.
- 4. Weatherup et al. J. Phys. Chem. Lett. 2016, 7, 1622.
- 5. Khatun et al. Adv. Mater. Interfaces 2021, 8, 2100662
- 6. Narayanan et al. Nature Commun. 2022, 13, 7237.
- 7. Gibson et al. Faraday Discuss., 2022, 236, 267.
- 8. Swallow et al. Nature Commun. 2022, 13, 6070.